



合肥腾泰阻燃新材料有限公司

HEFEI TENGTAI FLAME RETARDANT NEW MATERIALS CO., LTD.

驻极母粒产品规格书

产品简介:

- 1、载体为 MI1500 的熔喷 PP，无需添置新设备，无需大幅调整现有熔喷无纺布生产工艺；
- 2、对喷丝模头的使用周期和寿命没有影响；
- 3、在同等的纤维细度和同等的克重的情况下，降低无纺布产品的阻力，同时提高无纺布产品的滤效。

性能指标:

项目	单位	TMZ895	TMZ895D	TMZ895Y
水分	%	≤0.2	≤0.2	≤0.2
熔点	℃	165±3	165±3	165±3
耐热温度	℃	280	280	280
气味	-	无味	无味	无味
建议添加量	%	2~5	1~2	4~5
特点		有机复合型	电气石型	耐油双效型

应用领域:

熔喷无纺布 PP 中提高滤效，普通 BFE 系列根据过滤率 90%、95%、99.97%建议添加 1.0%-2.0%、PFE 系列根据过滤率 90%、95%、99.97%建议添加 2.0%-4.0%，如果需要提高过油性，添加量需适当提高；使用时需要与熔喷 PP 粒子按比例均匀混合；驻极效率与熔喷原料、喷布工艺、驻极设备、驻极工艺等因素相关，需要根据实际工艺调整添加比例。

包装储运:

净重 25 kg/包。不属于危险品，避光、防水运输，常规室温、防水储存。

免责声明: 本资料所提供的数据，为实验室测试典型数据，仅供参考，不作为正式质保凭证。用户有责任对所购我公司产品进行全面实验，以验证其是否符合自己工艺和性能标准要求。由于对发出的产品的应用和加工均非我公司所能掌控，所以期间事由一概由用户本身负责。

Disclaimer: The data provided in this document are typical data of laboratory test and are for reference only, not as a formal warranty certificate. Users are responsible for the purchase of our company's products to conduct a comprehensive experiment, to verify their process and performance standards. Due to the application and processing of the products we send all nonself company can control, so during the subject entirely by the user itself responsible.

以上内容由合肥腾泰阻燃新材料有限公司编制和负责解释，并保留根据需要更改本文内容的权利，请参考最新版本资料。

本文发布时间：2020 年 7 月。如您需要了解更多信息，请浏览 <http://hftzr.cn/>

电话: 15375068887

E-mail: ms.hu@enhand.cn